



- The flooring shall be Polyflor Camaro PU, as supplied by Polyflor Ltd. of Manchester, England.
- The flooring shall be flexible PVC tile and plank flooring in 2.0mm thickness.
- It shall have the following laminated construction: circa 0.3mm clear PVC wear layer with a polyurethane surface treatment, circa 0.07mm print film layer, and circa 1.63mm backing ply.



- In accordance with EN 649, the in-use classification must be at least 23/31 as described in EN 685: i.e. domestic areas with heavy use; commercial areas with low or intermittent use.
- In respect of flame spread, the flooring shall have been fully tested to EN 13501-1 and certified as having Class Bfl-S1, achieving the criteria EN ISO 9239-1 $\geq 8\text{kw/m}^2$ and the mandatory requirement of EN ISO 11925-2 pass.
- The product's weight should not be more than 3600g/m².
- In respect of light fastness, the flooring shall have been fully tested to ISO 105-B02 Method 3 as having a pass to ≥ 6 .



- The manufacturer of the floorcovering must be in possession of a valid quality systems certificate, showing compliance with BS EN ISO 9001: 2000.
- The manufacturer of the floorcovering must be in possession of a valid environmental certificate, showing compliance with ISO 14001.



- A moisture test must be carried out, to ensure that the subfloor has dried out to a level consistent with the application of vinyl flooring. The test should be carried out using a hygrometer, in accordance with the instructions in BS 8203. The result should not exceed 75%RH, once equilibrium has been achieved.
- The adhesive used must be approved by Polyflor, to ensure full product compatibility.
- Products must be fully conditioned to the environment in which they are to be installed. See Polyflor installation instructions for details.
- Installation must be carried out in accordance with BS 8203 and the instructions of Polyflor.
- Suitable for use with underfloor heating up to 27°C. See Polyflor installation instructions for details
- The flooring will achieve a BRE Global Environmental A+ Rating ENP 429 in the Green Guide to Specification.
NOTE: The subtle blending of shades and graining variation can best be obtained by the random shuffling of 3-4 packs of tiles.



- Polyflor Camaro PU is suitable for use in any domestic situation and moderate commercial areas .
On-floor temperatures in conservatories can become quite high. It is strongly advised that, in such situations, a Polyflor recommended high temperature adhesive is used. For further information and advice on specific applications, consult Polyflor Customer Technical Services on +44 (0)161 767 1912, or email tech@polyflor.com.



- At the date of issue the data presented is correct. However, Polyflor Ltd. reserve the right to make changes which do not adversely affect performance or quality.

CAMARO™
FLOORING COLLECTION



PRODUCT SPECIFICATION

POLYFLOR LTD. PO BOX 3 RADCLIFFE NEW ROAD WHITEFIELD MANCHESTER M45 7NR UK
UK SALES DIRECT: +44 (0)161 767 1122 UK SAMPLE REQUESTS: +44 (0)161 767 2551
EXPORT SALES DIRECT: +44 (0)161 767 1913 TECHNICAL SUPPORT: +44 (0)161 767 1912
RECEPTION: +44 (0)161 767 1111 UK FAX: +44 (0)161 767 1128
EXPORT FAX: +44 (0)161 767 1166 E-MAIL: INFO@POLYFLOR.COM
WEBSITE: WWW.POLYFLOR.COM

James Hallett
FLOORING



2006

POLYFLOR™
COVERING THE WORLD